

Valvoline Performance Products – Tectyl

Version: TE050/02

Tectyl™ 4D750

Premium ultra-low VOC containing, hollow section, corrosion preventive compound.

Tectyl 4D750 is a resin/oil based, light yellow, liquid corrosion preventive compound.

Tectyl 4D750 is formulated with a minimum of volatile organic components.

Tectyl 4D750 is designed for industrial application giving good penetration into folds, flanges and cracks, making it very suitable as a corrosion protective for the inside of car doors and other hollow sections of cars and rolling equipment.

Tectyl 4D750 cures to a light yellow, translucent, semi-soft film.

Approvals/Performance levels

Tectyl 4D750

Accelerated Corrosion tests:

@ Average recommended DFT

Accelerated Corrosion tests:

Salt Spray; 5 % NaCl @ 35°C; ISO 9227 NSS
(Q-Panels, Type R, ASTM A1008)

15+ days

Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH
(Q-Panels, Type R, ASTM A1008)

50+ days

Tectyl 4D750 is Approved according to TR 338:2010, **SFS 4086:2006**, 02-12-2010
Granted certificate by Inspecta Sertifionti Oy for Anti-corrosion agents for internal hollow.

As Tectyl 4D750 is a chemical drying product, the cure time is depending on the application and environmental conditions

Applications

Surface Preparation:

The maximum performance of TECTYL 4D750 can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale and a substrate temperature of 10-35 °C at the time of product application.

Application:

TECTYL 4D750 is formulated to be used as supplied. DO NOT THIN TECTYL 4D750. DO NOT FREEZE TECTYL 4D750 while curing. Tectyl 4D750 can be applied by low pressure air spray application. As Tectyl 4D750 is a chemical drying product, care should be taken to avoid prolonged contact of the product in the container with air (oxygen) as much as possible. During use this can be achieved by binding the plastic innerliner around the suction tube with a plastic binder. If not in use, keep the container tightly closed!

Removal:

TECTYL 4D750 can be removed with mineral spirits or any similar petroleum solvent. Also Tectyl Biocleaner can be used to remove Tectyl 4D750.

Features & Benefits

Superior Protection

At the recommended DFT, the hollow sections are protected against corrosion.

Efficient

With a DFT of only 40 microns, Tectyl 4D750 is an efficient corrosion protection, protecting a large area with little amount of the product.

Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit www.tectyl-europe.com

Typical properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

Tectyl 4D750	
Flash Point, PMCC [°C]	>180
Density @ 20°C [kg/ltr]	0,91
Recommended Dry Film Thickness over metal profile [microns]	40
Theoretical coverage @ recommended DFT [m ² /ltr]	24,4
Non Volatile [weight %]	98
Viscosity; Brookfield @ 20°C @ 2 RPM [mPa.s] [cP]	6000
@ 20 RPM [mPa.s] [cP]	1500
Penetration [mm] (In house test)	40
Dry to touch time @ 20°C [hours]	72
Volatile Organic Compound Content ISO 11890-2 (10.4) [g/ltr]	50

This information only applies to products manufactured in the following location(s): Europe

™ Trademark of Valvoline, registered in various countries © 2017

All statements, information and data presented herein are believed to be accurate and reliable, but are not to be taken as a guarantee, an express warranty, or an implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which Ellis Enterprises B.V. and its affiliates assume legal responsibility.

Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet

<http://sds.valvoline.com>

Protect the environment

Comply with local regulations. Comply with local regulations. Do not discharge into drains, soil or water.

Storage

Tectyl 4D750 should be stored at temperatures between 10-35 °C. Mild agitation is recommended prior to use.

Due to its composition Tectyl 4D750 can be subject to postproduction viscosity changes during storage.

Under proper storage conditions Tectyl 4D750 is best before 6 months after production date.

Caution

Refer to the Safety Data Sheet for additional handling and first aid information.

Note

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Typical Properties section. If a primer, other than a Valvoline recommended product is required, written authorization must be obtained from Valvoline.

Replaces – TE050/01